



Nylon 12CF

FDM Nylon 12CF™ is a carbon-filled thermoplastic with excellent structural characteristics. The material is comprised of a blend of Nylon 12 resin and chopped carbon fiber, at a loading of 35% by weight. This combination produces one of the strongest thermoplastics in the FDM material portfolio. It has the highest flexural strength of any FDM thermoplastic, resulting in the highest stiffness-to-weight ratio.

Appropriate uses include strong but lightweight tooling applications and functional prototypes in the aerospace, automotive, industrial and recreational manufacturing industries.

Mechanical Properties	Test Method	XZ Axis	ZX Axis
Tensile Strength, Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	63 MPa (9,190 psi)	29 MPa (4,170 psi)
Tensile Strength, Ultimate (Type 1, 0.125", 0.2"/min)	ASTM D638	76 MPa (10,960 psi)	34 MPa (4,990 psi)
Tensile Modulus (Type 1, 0.125", 0.2"/min)	ASTM D638	7.6 GPa (1,100 ksi)	2.3 GPa (330 ksi)
Tensile Elongation at Break (Type 1, 0.125", 0.2"/min)	ASTM D638	1.9%	1.2%
Tensile Elongation at Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	0.9%	1.1%
Flexural Strength (Method 1, 0.05"/min)	ASTM D790	142 MPa (20,660 psi)	58 MPa (8,430 psi)
Flexural Modulus (Method 1, 0.05"/min)	ASTM D790	10.3 GPa (1,500 ksi)	2.07 GPa (300 ksi)
Flexural Strain at Break (Method 1, 0.05"/min)	ASTM D790	3%	3%
IZOD Impact, notched (Method A, 23 °C)	ASTM D256	85 J/m (1.6 ft-lb/in)	21 J/m (0.4 ft-lb/in)
IZOD Impact, un-notched (Method A, 23 °C)	ASTM D256	307 J/m (5.8 ft-lb/in)	85 J/m (1.6 ft-lb/in)
Compression Strength, Ultimate (Method 1, 0.050 in./min)	ASTM D695-15	67 MPa (9,670 psi)	92 MPa (13,310 psi)
Compression Modulus (Method 1, 0.050 in./min)	ASTM D695-15	2.7 GPa (387 ksi)	2.2 GPa (314 ksi)

Thermal Properties	Test Method	Value
Heat Deflection (HDT) @ 264 psi	ASTM D648	143 °C (289 °F)
Glass Transition Temperature (Tg)	ASTM D7426-08	41 °C (105 °F)
Coefficient of Thermal Expansion (flow) at 104 °F (40 °C)	ASTM E831	25 µm/(m·°C) (14 µin/(in·°F))
Coefficient of Thermal Expansion (flow) at 212 °F (100 °C)	ASTM E831	27 µm/(m·°C) (15 µin/(in·°F))
Coefficient of Thermal Expansion (xflow) at 104 °F (40 °C)	ASTM E831	150 µm/(m·°C) (83 µin/(in·°F))
Coefficient of Thermal Expansion (xflow) at 212 °F (100 °C)	ASTM E831	300 µm/(m·°C) (167 µin/(in·°F))